

103 LANKOMUR PRÊT



PRODUCT FEATURES

- ▶ Application thickness: 0.3 to 4 mm
- ▶ Ready-to-use paste
- ▶ Excellent trowelability
- ▶ Perfectly smooth finish
- ▶ Can be covered after just 24-48 hours

CONSUMPTION

- ▶ 1.8 kg/m²/mm

PACKAGING

- ▶ 25 kg bucket

STORAGE

- ▶ 12 months

from date of manufacture if stored in unopened original packing in dry, frost-free conditions

WARRANTY

- ▶ Manufacturer's liability



DESCRIPTION

- Ready-to-use skim-smoothing levelling paste for filling bubbles and finishing raw concrete in thicknesses ranging from 0.3 to 4 mm.
- The paste produces a smooth finish and eliminates minor surface blemishes.

USES

- Interior and exterior walls
- Ceilings

■ PERMISSIBLE SUBSTRATES

Interior/Exterior

- Shuttered concrete
- Rendered masonry
- Concrete soffits
- Precast concrete
- Pâte de verre

Interior only

- Cellular concrete primed with **REVLANE+ RÉGULATEUR** or a solution made up with 1 part **751 LANKO LATEX** + 2 parts water.
- Brick blocks
- Plaster blocks, plaster primed with **REVLANE+ RÉGULATEUR**
- Plasterboard

■ SUITABLE COVERING MATERIALS

- Thick synthetic finish coats
- Paint (except mineral paint)
- Wallpaper
- Fabric
- Bonded plastic coverings
- Ceramic coverings bonded with cement-free paste adhesive (interior only, maximum format 1 200 cm², minimum render thickness 3 mm).

SPECIFICATIONS

- **Ingredients:** synthetic resins, mineral filler and admixtures
- **Appearance:** grey paste
- **Ready-to-use:** do not add hydraulic binder
- **Particle size:** < 0.1 mm
- **Paste density:** 1.8
- **pH:** 9

PERFORMANCE CHARACTERISTICS

- **Bonding strength (1):** (MPa) for 1 mm thickness

Period	28 days
Concrete substrate	> 1 MPa

INSTRUCTIONS

■ SUBSTRATE PREPARATION

- The substrate must be clean, sound, dust-free and without any traces of oil, laitance, curing compound etc.
- Dampen substrate prior to application.
- Overplus, seams and rock pockets exceeding 4 mm must be treated prior to application.

Pâte de verre

- Check the surface state and remove any loose or flaking parts.
- Wash with a soda-based detergent, rinse and leave to dry.
- Apply a 1st coat to get a reasonably level surface.
- Apply the 2nd (finish) coat 24 hours later.

■ PRODUCT PREPARATION

- Ready-to-use paste. No water or binder must be added.

■ APPLICATION

Manual

- Apply small quantities of **103 LANKOMUR PRÊT** with a stainless steel float.
- A minimum of 2 coats are required to obtain a satisfactory surface
- Allow 2 hours drying time between coats at 20°C.
- Minimum curing time before covering: 24-48 hours depending on substrate type and covering material.

Machine

- **103 LANKOMUR PRÊT** can also be sprayed onto the substrate using a spraying machine (e.g. EUROPRO 8P by EUROMAIR).

(1) Average laboratory value provided as a general guide.

PRECAUTIONS

- Do not apply to a damp or frozen substrate or in freezing conditions.
- Thicknesses of 4mm may only occasionally be applied, e.g. when filling bug holes and bubbles.
- Do not use on submerged substrates.
- Do not cover with a hydraulic binder-based mortar.
- Do not mix with any other product.
- Any excess product that has been in contact with the substrate must not be returned to the bucket.
- Do not add hydraulic binder or any other admixture
- Refer to the Safety Data Sheet.

TECHNICAL ASSISTANCE: ParexGroup S.A. will, on request, provide information and assistance to companies in relation to the specific use of a product. Such assistance shall not be assimilated with structural design and conception, nor the compliance of substrates, nor as a control of usage rules in force.

TECHNICAL DATA SHEET ISSUED - September 2017

The information provided in this document results from our knowledge of the products and our experience. Prior to application, customers and users are requested to check that they are in possession of the latest version of this document. Please check for updates at www.parexlanko.com

PAREXGROUP S.A. 19 place de la Résistance - CS 50053
92445 Issy-les-Moulineaux Cedex - Tél. (33) 01 41 17 20 00
Technical information : 0 826 08 68 78 (0.15 €/min + phone call price)