

# 165 PROLIPRIM UNIVERSEL



### PRODUCT FEATURES

- ▶ Multi-purpose: suitable for all substrates
- ▶ Enhances substrate cohesion
- ▶ Improves bonding strength of levelling mortar
- ▶ Compatible with anhydrite screed

### CONSUMPTION

- ▶ 100-200 g/m<sup>2</sup> depending on substrate porosity

### PACKAGING

- ▶ 2 litre, 5 litre and 20 litre containers
- ▶ Pallet containing 28 x 20 litre containers (560 kg)

### STORAGE

- ▶ **12 months** from date of manufacture if stored in unopened original packaging in frost-free conditions and away from high temperatures

### WARRANTY

- ▶ Manufacturer's liability

**TECHNICAL ASSISTANCE** ParexGroup S.A. will, on request, provide information and assistance to companies in relation to the specific use of a product. Such assistance shall not be assimilated with structural design and conception, nor the compliance of substrates, nor as a control of usage rules in force.

**TECHNICAL DATA SHEET ISSUED - September 2017**  
The information provided in this document results from our knowledge of the products and our experience. Prior to application, customers and users are requested to check that they are in possession of the latest version of this document. Please check for updates at [www.parexlanko.com](http://www.parexlanko.com).

**PAREXGROUP S.A.** 19 place de la Résistance - CS 50053  
92445 Issy-les-Moulineaux Cedex - Tél. (33) 01 41 17 20 00  
Technical information : 0 826 08 68 78 (0.15 €/min + phone call price)

# PAREXLANKO



### DESCRIPTION

- **165 PROLIPRIM UNIVERSEL** is an extremely versatile product. It regulates substrate porosity, thus preventing the formation of bug holes and facilitating the application of floor mortar. It also enhances the bonding strength of levelling mortar or adhesive to smooth or closed substrates. It ensures good adherence of floor mortars and adhesives on anhydrite screed.

### USES

- Interior & exterior walls
- Interior & exterior floors
- **PERMISSIBLE SUBSTRATES**
  - Floating cement screed
  - Bonded cement screed
  - Fluid anhydrite or cement screed
  - Concrete flooring
  - Prefabricated elements
  - Cellulose fibre board (e.g. Fermacell)
  - Cement panels (e.g. Hydropanel)
  - Plaster coating
  - Plasterboard
  - Lightweight concrete and mortar
  - Cellular concrete
  - Old adhesive
  - Semi-flexible plastic tiles
  - Wood panels (CTB-H/CTB-X/OSB3)
  - Existing floor tiles
  - Sanded paintwork

### ■ ASSOCIATED PRODUCTS

- Smoothing mortar
- Levelling mortar
- Self-levelling mortar
- Mortar adhesive
- Decorative adhesive
- **596 PROLICOAT\*** (Undertile Protection System)
- **588 ENDUIT D'ÉTANCHÉITÉ\*** (liquid waterproofing system)

### SPECIFICATIONS

- **Composition:** aqueous dispersion of acrylic polymers.
- **Appearance:** white liquid
- **Density:** 1 ± 0.1
- **pH:** 8.5 ± 1
- **Classification:** non-flammable, non-toxic

\* Refer to the relevant Technical Data Sheet.

### PRECAUTIONS

- Temperature range for use: 5°C - 30°C.
- Not for use in swimming pools.
- Clean fresh product with water
- Clean dry product with steam
- Gloves and eye protection should be worn.
- Refer to the Safety Data Sheet.

### INSTRUCTIONS

#### ■ SUBSTRATE PREPARATION

- Substrates must be compliant with building regulations in force, e.g. for France, DTU and CPT standards and CSTB renovation guidelines.
- Substrates must be clean, solid, sound and free of cracks, oil and traces of plaster, wax and any other product which may adversely affect bonding.
- Scrape, brush off or vacuum-clean all traces of plaster, laitance, paint, non-bonded adhesive and mortar.
- Substrates bearing excessive traces of wax, grease or paint must be stripped.
- All substrates must be thoroughly dusted.

#### Tiles and paintwork

- De-sheen gloss paint and enamel tiles. Remove dust.
- Remove glaze left by grease and cleaning products (wax, polish, etc...) using a soda-based cleaning solution.
- Rinse thoroughly and leave to dry.

#### Anhydrite screed and highly porous substrates

- Check that the moisture content is compliant with the screed manufacturer's specifications.
- Remove surface sheen by brushing or sanding. Remove all traces of dust.
- Apply 2 coats of primer, at least 30 minutes apart.

#### ■ PRODUCT PREPARATION

- **165 PROLIPRIM UNIVERSEL** is ready to use and must not be diluted.

#### ■ APPLICATION

- Apply a regular, evenly-spread coat of **165 PROLIPRIM UNIVERSEL** with a roller, a brush or a rubber spreader. Take care to cover the entire surface of the substrate and to avoid applying too much or too little.

#### Drying time

- 30 minutes to 2 hours depending on substrate type, ambient temperature and relative humidity.
- **165 PROLIPRIM UNIVERSEL** can be covered as soon as it is touch-dry.

#### Covering time

- The dry coat must be covered within 24 hours. If this period of time is exceeded a new coat of primer must be applied.