

- INTEGRAL WATERPROOFING ADMIXTURE (POWDER)



PRODUCT FEATURES

- ▶ Waterproofing agent for mortars and concretes, improves plasticity
- ▶ Reduces formation of efflorescence and saltpeter

CONSUMPTION

- ▶ 1 x 250 g dose for 1 x 35 kg bag of cement

REFERENCE DOCUMENT

- ▶ CE Performance statement

PACKAGING

- ▶ 250 g ready-to-add dose

STORAGE

- ▶ **30 months** from date of manufacture if stored in unopened original packing in dry conditions

WARRANTY

- ▶ Manufacturer's liability

TECHNICAL ASSISTANCE: ParexGroup S.A. will, on request, provide information and assistance to companies in relation to the specific use of a product. Such assistance shall not be assimilated with structural design and conception, nor the compliance of substrates, nor as a control of usage rules in force.

TECHNICAL DATA SHEET ISSUED - September 2017

The information provided in this document results from our knowledge of the products and our experience. Prior to application, customers and users are requested to check that they are in possession of the latest version of this document. Please check for updates at www.parexlanko.com.

PAREXGROUP S.A. 19 place de la Résistance - CS 50053 92445 Issy-les-Moulineaux Cedex - Tél. (33) 01 41 17 20 00
 Technical information : 0 826 08 68 78 (0,15 €/min + phone call price)

PAREXLANKO

323 LANKOFUGE POWDRE



DESCRIPTION

- Chloride-free powder admixture that considerably reduces capillarity of mortar and concrete and improves waterproofing capability.
- **323 LANKOFUGE POWDRE** is suitable for use with all types of cement (with the exception of high alumina cement).

USES

■ WATERPROOFING

- Façade mortars exposed to driving rain
- Masonry joints
- Foundation topping screed

■ WATERTIGHT SEALING OF DIFFERENT STRUCTURES

- Concrete foundations below water table level
- Buried concrete
- Concrete water tanks and basins
- Shaft linings, tanking

SPECIFICATIONS

- **Appearance:** white powder
- **Apparent density:** < 1
- **Chloride ion content:** ≤ 0.10%

INSTRUCTIONS

■ PRODUCT PREPARATION

- **323 LANKOFUGE POWDRE** is sprinkled onto the dry mixture and then carefully and evenly blended in.

PRECAUTIONS

- Temperature range for use: + 5°C to + 35°C.
- For use with clean sand and aggregates with a controlled particle size.
- Mortar composed of minimum 500 kg of cement (or 350 kg of cement and 150 kg of lime).
- Cement dose = 350 kg cement minimum per m³.
- Mix to a plastic consistency.
- Do not use with high alumina cement.
- Do not use lime in mixes for waterproofing tanks and basements.
- Refer to the Safety Data Sheet.