

- WATER-BASED SILICONE TILING MASTIC



PRODUCT FEATURES

- ▶ Very easy to smooth, cleans with water
- ▶ Bonds to damp substrates
- ▶ Odourless
- ▶ Joint protected from mould
- ▶ Ideal for peripheral joints

CONSUMPTION

- ▶ 5 mm joint: 12 metres approx. for one cartridge

PACKAGING

- ▶ 300 ml plastic cartridge

STORAGE

- ▶ **18 months** from date of manufacture if stored in unopened original packaging protected from frost and high temperatures

WARRANTY

- ▶ Manufacturer's liability

626 SILICONE CARRELEUR



DESCRIPTION

- Single-component water-based mastic.
- Dries by simple evaporation of water and then cross-links, without emitting any odour or chemical product.
- Good performance in terms of elongation and elastic recovery.
- Excellent mould resistance.

USES

- Tiling, plumbing and bathroom applications.
- Peripheral joints.
- Weatherstripping of cracks.
- Indoor/outdoor use.

NOT SUITABLE FOR

- Building aquariums
- Applications in contact with foodstuffs
- Floor joints subjected to high abrasion
- Acrylic-based sanitary equipment or items made of materials that may exude certain components over time (e.g. Nitril, rubber, EPDM...)
- Substrates prone to water stagnation

SPECIFICATIONS

- **Colours:** white, grey, light grey, black and beige
- **Appearance:**
 - before cross-linking: paste
 - after cross-linking: elastic mass
- **Density:** 1.35
- **Shore A hardness:** 20
- **Skin formation time:** 12 min approx.
- **Drying time:** 72 hours (5 mm bead)
- **Volume loss after drying:** 12% approx.
- **Elongation at breaking point:** 400% approx.
- **Elastic recovery:** 80% approx.
- **Application temperature:** + 5°C to + 40°C
- **Service temperature:** - 50°C to + 120°C

INSTRUCTIONS

■ SUBSTRATE PREPARATION

- Application surfaces must be clean and dust-free and without any traces of grease or any other substance that may impair bonding...
- If necessary, insert a joint backing so as to obtain a mastic bead that is approximately 1/2 the width of the joint to be filled.
- **626 SILICONE CARRELEUR** can be used on damp substrates.

■ APPLICATION

- Ensure that the joint is completely filled. Smooth the mastic with a damp tool (e.g. putty knife, sponge...) before the surface film forms.
- Clean mastic spills and tools with clean water.
- Once dry and cross-linked, mastic can be removed by scraping (e.g. with a razor blade).
- Perform a preliminary test before painting over.

TECHNICAL ASSISTANCE: ParexGroup S.A. will, on request, provide information and assistance to companies in relation to the specific use of a product. Such assistance shall not be assimilated with structural design and conception, nor the compliance of substrates, nor as a control of usage rules in force.

TECHNICAL DATA SHEET ISSUED - September 2017

The information provided in this document results from our knowledge of the products and our experience. Prior to application, customers and users are requested to check that they are in possession of the latest version of this document. Please check for updates at www.parexlanko.com

PAREXGROUP S.A. 19 place de la Résistance - CS 50053
92445 Issy-les-Moulineaux Cedex - Tél. (33) 01 41 17 20 00
Technical information : 0 826 08 68 78 (0.15 €/min + phone call price)

PAREXLANKO

PRECAUTIONS

- Do not apply when temperatures fall below + 5°C, owing to the risk of substrate frosting.
- In view of the wide range of materials available, a representative test should be carried out prior to application.
- Not recommended for bonding mirrors to substrates.
- **626 SILICONE CARRELEUR** is not to be used as an adhesive.
- Refer to the Safety Data Sheet.