



### PRODUCT FEATURES

- ▶ Reduces the risk of cracking
- ▶ Protects fresh mortar or concrete from drying out
- ▶ Reduces crazing and shrinkage

### CONSUMPTION

- ▶ Standard use: 0.185 litre/m<sup>2</sup>
- ▶ Maximum dosage: 0.28 litre/m<sup>2</sup>  
i.e. 3.6 to 5.4 m<sup>2</sup>/litre

### REFERENCE DOCUMENTS

- ▶ Standard NF P 18-370

### PACKAGING

- ▶ 20 litre container

### STORAGE

- ▶ **24 months**  
from date of manufacture if stored in unopened original packing in dry, frost-free conditions and away from heat sources and high temperatures

### WARRANTY

- ▶ Manufacturer's liability

# 742 LANKOCURING



### DESCRIPTION

- **742 LANKOCURING** forms a continuous protective film on the surface of fresh mortar and concrete.
- This film delays the evaporation of water content in strong sunlight and windy conditions and promotes correct binder hydration, even at the surface.

### USES

- All cases in which climatic conditions (sun, wind) accelerate the evaporation of water used in mixing.
- Structures with a high surface/volume ratio.
- For reducing cracking and shrinkage in the following situations:
  - road and motorway surfaces, bridges, embankments, canals, airport runways
  - protection of concrete walkways, terraces and flooring.

### SPECIFICATIONS

- **Ready-to-use**
- **Appearance:** straw-coloured liquid
- **Density:** 0.84 ± 0.02
- **Flash point:** > + 40°C

### INSTRUCTIONS

- **742 LANKOCURING** must be sprayed pure onto the surface of the concrete or mortar as soon as it begins to take on a matt appearance.
- Ensure that substrates are not seeping with water prior to application. Remove any surface water.
- If a coating is to be applied to the surface, **742 LANKOCURING** should be removed by vigorous brushing or light sanding after drying.
- The product film will disappear over time as a result of weathering or abrasion.

**TECHNICAL ASSISTANCE.** ParexGroup S.A. will, on request, provide information and assistance to companies in relation to the specific use of a product. Such assistance shall not be assimilated with structural design and conception, nor the compliance of substrates, nor as a control of usage rules in force.

#### TECHNICAL DATA SHEET ISSUED - September 2017

The information provided in this document results from our knowledge of the products and our experience. Prior to application, customers and users are requested to check that they are in possession of the latest version of this document. Please check for updates at [www.parexlanko.com](http://www.parexlanko.com)

**PAREXGROUP S.A.** 19 place de la Résistance - CS 50053  
92445 Issy-les-Moulineaux Cedex - Tél. (33) 01 41 17 20 00  
Technical information : 0 826 08 68 78 (0.15 €/min + phone call price)

# PAREXLANKO

### PRECAUTIONS

- **742 LANKOCURING** is a solvent-based product and must therefore be used in well-ventilated conditions, especially in confined environments.
- Prior to application, ensure that all surface moisture has been removed.
- Suitable Personal Protection Equipment must be worn.
- Do not expose to a naked flame.
- Refer to the Safety Data Sheet.