



PRODUCT FEATURES

- ▶ Protection of steel reinforcing bars
- ▶ Single component
- ▶ Can be covered within 2 hours

CONSUMPTION

- ▶ Approximately 0.1 litre/m²

REFERENCE DOCUMENTS

- ▶ APPLUS test report
- ▶ CE Performance Statement

PACKAGING

- ▶ 3 litre can

STORAGE

- ▶ **24 months**
from date of manufacture if stored in unopened original packing protected from frost, high temperatures and heat sources

WARRANTY

- ▶ Manufacturer's liability

TECHNICAL ASSISTANCE: ParexGroup S.A. will, on request, provide information and assistance to companies in relation to the specific use of a product. Such assistance shall not be assimilated with structural design and conception, nor the compliance of substrates, nor as a control of usage rules in force.

TECHNICAL DATA SHEET ISSUED - September 2017

The information provided in this document results from our knowledge of the products and our experience. Prior to application, customers and users are requested to check that they are in possession of the latest version of this document. Please check for updates at www.parexlanko.com

PAREXGROUP S.A. 19 place de la Résistance - CS 50053
92445 Issy-les-Moulineaux Cedex - Tél. (33) 01 41 17 20 00
Technical information : 0 826 08 68 78 (0,15 €/min + phone call price)

PAREXLANKO

760 LANKOPASSIV



DESCRIPTION

- Single component solvent-base paint for the protection of concrete-reinforcing steel bars (rebars) against corrosion.

USES

- Passivation of steel rebars prior to application of hydraulic mortars, especially those belonging to the LANKOREP range.

SPECIFICATIONS

- **Appearance:** silky
- **Colour:** fawn
- **Density:** 1.5
- **Dry content by weight:** 72%
- **Conditions at + 20°C and 50% relative humidity:**
 - Dust-free: 5 min
 - Touch-dry: 15 min
- **Coverable:** 2 hours
- **Compliant with corrosion protection test as described in Standard EN 15183**

INSTRUCTIONS

■ SURFACE PREPARATION

- Clear out space around corroded rebars in order to enable optimum coating.
- Remove all traces of rust (using a metal brush or by sandblasting).
- Dust off all surfaces to be repaired.
- Rebars must be perfectly dry and grease-free during application.

■ PRODUCT PREPARATION

- After opening the container, stir **760 LANKOPASSIV** thoroughly to ensure even distribution.

■ APPLICATION

- Using a brush, apply a thick coat to the prepared rebars.
- Avoid overflow onto the surrounding concrete.
- The repair mortar should only be applied once **760 LANKOPASSIV** has dried, i.e. at least 2 hours after application.
- The treated rebars can be left for several days. In this case, check that the coating has not deteriorated. If necessary, apply a second coat of **760 LANKOPASSIV**.

■ EQUIPMENT CLEANING

- Clean tools with **725 LANKODILPOX**.

PRECAUTIONS

- Temperature range for use: + 5°C to + 35°C.
- Protective gloves should be worn.
- Refer to the Safety Data Sheet.