

CONCRETE REPAIR WORK

- FIBRE-REINFORCED SHRINKAGE-COMPENSATING REPAIR MORTAR



PRODUCT FEATURES

- ▶ Fine and rapid
- ▶ Application thickness: 2-70 mm per coat
- ▶ Can be painted over within 24 hours
- ▶ NF030 "Repair products" label

CONSUMPTION

- ▶ 2 kg/m² per mm thickness

REFERENCE DOCUMENTS

- ▶ Approved «Repair Product» in accordance with Standard NF030
- ▶ CE Performance Statement

PACKAGING

- ▶ 25 kg long storage bag

STORAGE

- ▶ 12 months from date of manufacture if stored in unopened original packing in dry conditions

WARRANTY

- ▶ Manufacturer's liability

TECHNICAL ASSISTANCE: ParexGroup S.A. will, on request, provide information and assistance to companies in relation to the specific use of a product. Such assistance shall not be assimilated with structural design and conception, nor the compliance of substrates, nor as a control of usage rules in force.

TECHNICAL DATA SHEET ISSUED - September 2017

The information provided in this document results from our knowledge of the products and our experience. Prior to application, customers and users are requested to check that they are in possession of the latest version of this document. Please check for updates at www.parexlanko.com

PAREXGROUP S.A. 19 place de la Résistance - CS 50053
92445 Issy-les-Moulineaux Cedex - Tél. (33) 01 41 17 20 00
Technical information - 0 826 08 68 78 (0,15 €/min + phone call price)

PAREXLANKO

770 LANKOREP FIN RAPIDE



DESCRIPTION

- **770 LANKOREP FIN RAPIDE** is a fine, single-component, fast-setting mortar.
- This shrinkage-compensating mortar is composed of sand, special cement, fibres and specific admixtures. The low porosity of **770 LANKOREP FIN RAPIDE** significantly delays the progression of carbonation.

USES

- Repair of concrete surfaces: spalling, honeycombing, stair nosing, precast elements, etc...
- Concrete restructuring: beams, slabs, posts, pillars, reservoir aprons and spillways, structures in marling zones.
- Reinforcement of weakened structures e.g. balconies, overhangs, cornices.
- Treatment of chamfers and seams prior to waterproofing.
- Treatment of passive cracks.

SPECIFICATIONS

- Active ingredients including hydraulic binders and synthetic fibres with no metal particles
- Grey ready-to-mix powder
- Particle size: 0-0.8 mm
- Hardened product density: 2.1 ± 0.1
- Abrams cone slump: 2.5 cm
- Bond strength by pull-off test in compliance with EN1542: ≥ 1.5 MPa
- Mortar pH: 12.5

PERFORMANCE CHARACTERISTICS

- Pot life: 35 min approx. at + 20°C
10 min approx. at + 30°C

Setting time (1)

Temperature	+ 20°C
Initial setting	1 h
Final setting	1 h 30

Mechanical strength (2) (MPa)

Period	1 day	28 days
Flexural	3	8
Compressive	15	40

INSTRUCTIONS

SUBSTRATE PREPARATION

- Ensure that the substrate is free of any traces of plant-based or mineral pollution, e.g. grease, oil, laitance, etc...
- Remove loose and damaged concrete by means of a suitable tool in order to obtain a clean, rough surface.
- Clear out concrete around corroded rebars in order to create space for inserting the product behind and around them. The boundaries of the surface to be repaired must be clearly defined.
- Brush, scrape or sandblast corroded rebars in order to remove non-adherent rust.
- Dust off all surfaces to be repaired.
- Soak the substrate prior to application (substrate must be damp but not seeping with water).

Rebar passivation

- As required, by local application of:
 - a slurry of **770 LANKOREP FIN RAPIDE** mixed with pure **751 LANKO LATEX** resin,
 - a passivating paint **760 LANKOPASSIV**
 - or, overall treatment by spray application of a corrosion inhibitor **761 LANKOSTEEL**.

MORTAR PREPARATION

- The mortar is made up by mixing **770 LANKOREP FIN RAPIDE** with clean water.
- Mix by hand with a trowel and trough or by machine (cement mixer or electric mixer).
- Mix for at least 3 minutes until a homogenous mixture has been obtained.
- No water must be added during application.

MORTAR APPLICATION

- Apply a first coat of **770 LANKOREP FIN RAPIDE** with a trowel, pressing firmly to ensure effective bonding and then build up the thickness to a maximum of 70 mm in one single operation.
- Dosage / Yield

Quantity	1 x 25 kg bag
Water	3.5 litres
Final volume	13 litres

(1) Average laboratory values provided as a general guide.

(2) Tests carried out in compliance with Standard EN 12190. Average laboratory values provided as a general guide.

PRECAUTIONS

- Temperature range for use: + 5°C to + 35°C.
- For applications in temperatures above + 20°C store bags in a cool place and use cold water for mixing.
- Do not apply in full sunlight or in windy conditions. Do not apply to a frozen or thawing substrate.
- Apply only to clean, sound, resistant substrates, free of loose material.
- Active cracks should be treated separately following a survey by the project manager.
- After finishing, protect the mortar from drying out by applying **742 LANKOCURING**, taking care to moisten but not soak the surface.
- Refer to the Safety Data Sheet.